

AD-A275 501



OFFICE OF NAVAL RESEARCH

FINAL REPORT

for

GRANT: N00014-90-J-1531

R & T Code 441p013

**S** DTIC  
ELECTE  
FEB 14 1994  
**A**

CELLULAR AND MOLECULAR APPROACHES TO POLYMER  
SYNTHESIS BY BACTERIA

ROBERT W. LENZ and R. CLINTON FULLER

University of Massachusetts  
Amherst, MA 01003

Polymer Science and Engineering Department (RWL)  
Department of Biochemistry and Molecular Biology (RCF)

1 JULY 1986 - 28 FEBRUARY 1993

DTIC QUALITY INSPECTED 1

Reproduction in whole, or in part, is permitted for any purpose of the  
United States Government.

This document has been approved for public release and sale, its  
distribution is unlimited.

94 2 09 072

94-04516



6899

## FINAL REPORT

GRANT #: N00014-90-J-1531

R&T CODE: 441p013

PRINCIPAL INVESTIGATORS: Drs. R.C. Fuller and R.W. Lenz

INSTITUTION: University of Massachusetts

GRANT TITLE: Cellular and Molecular Approaches to Polymer Synthesis by Bacteria

REPORTING AND AWARD PERIOD: 1 July 1986 - 28 February 1993

OBJECTIVE: The objective of this project was a multi-disciplinary study of the biosynthesis, regulation and materials properties of microbial poly- $\beta$ -hydroxyalkanoates (PHAs).

APPROACH: Three principal areas were investigated, including: (1) the production of new poly- $\beta$ -hydroxyalkanoates, PHAs, (2) the structure and function of proteins associated with the PHA inclusion bodies in the cells, and (3) the enzymatic degradation of PHAs.

In our overall studies on the production of new PHAs, we investigated the growth rates, polymer yields and polymer compositions obtained with two anaerobic, phototrophic bacteria, *Rhodobacter sphaeroides* and *Rhodospirillum rubrum*, and one aerobic bacterium, *Pseudomonas oleovorans*. The first two produced PHAs with short chain  $\beta$ -alkyl substituents (primarily methyl and ethyl) while the last produced PHAs with long alkyl chains ( $C_4$  -  $C_8$ ) at the  $\beta$ -position. *P. oleovorans* was also much more versatile in the types of polyesters it could produce, especially in its ability to produce PHAs containing  $\beta$ -substituents with terminal functional groups, including ester, phenyl, cyano and vinyl groups and bromine atoms. However, *R. sphaeroides* showed a capacity of accumulating PHA in high quantities, and deuterated PHAs were formed by this bacterium when it was grown on  $d_3$ -acetate. Similarly, *R. rubrum* was able to incorporate units with varying amounts of the methyl- and ethyl-containing units, and the production of copolymers appeared to be the rule rather than the exception for this bacterium.

When *P. oleovorans* was grown on *n*-alkanoic acids, the formation of intracellular PHAs was observed only for hexanoate and the higher *n*-alkanoic acids. The maximum isolated polymer yields were approximately 40% of the cellular dry weight when grown on either octanoate or nonanoate. In most cases, the major repeating unit in the polymer had the same chain length as the *n*-alkanoic acid used for growth, but units with two carbon atoms less or more than the acid used as carbon source were also generally present in the polyesters formed. Indeed, copolymers containing as many as six different types of  $\beta$ -hydroxyalkanoate units could be formed. The weight average molecular weights of the PHA copolymers produced by *P. oleovorans* ranged from 90,000 to 370,000.

*P. oleovorans* could be grown on a wide variety of functionalized organic compounds as either a sole carbon source or in mixtures with traditional carbon sources to produce functionalized PHAs. Among these substrates were methyl-branched alkanolic acids,  $\omega$ -bromoalkanoic acids,  $\omega$ -

Dist	Special
A-1	

cyanoalkanoic acids,  $\omega$ -phenylalkanoic acids and terminally unsaturated alkanolic acids. For example, three different  $\omega$ -bromoacids were evaluated as substrates separately, including 6-bromohexanoic acid (6-BH), 8-bromooctanoic acid (8-BO) and 11-bromoundecanoic acid (11-BU). Growth was much faster with 11-BU than with 8-BO, and there was no growth with 6-BH. These results showed that cell growth was favored only when the distance between the functional substituent (Br) and the bioreactive group (COOH) was sufficiently long. However, no PHA granules were observed in cells grown on any of these bromoalkanoic acids, so the three bromoalkanoic acids were combined with equimolar amounts of *n*-nonanoic acid and fed to *P. oleovorans*, which had been grown initially on *n*-nonanoic acid. PHA granules were observed in the cells grown on all of the 1:1 molar mixtures, and the amount of  $\omega$ -bromo- $\beta$ -hydroxyalkanoate units was as high as approximately 38 mole % when a mixture of 1:1 moles of nonanoic acid to 11-BO was used as the carbon source.

Very similar results were obtained with the methyl-branched substrates. That is, *P. oleovorans* was grown on a series of branched alkanolic acids, including 6-methylnonanoic acid (6-MNA), 7-methylnonanoic acid (7-MNA), 8-methylnonanoic acid (8-MNA), 9-methyldecanoic acid (9-MDA), 7-methyldecanoic acid (7-MDA) and 2,6-di-methylhept-5-enoic acid (2,6-DMHA). Polyesters were obtained from growth on pure 9-MDA, 8-MNA, 7-MNA, 6-MNA, but not from 7-MDA and 2,6-DMHA. Mixtures of *n*-nonanoic acid (*n*-NA) and either 7-MDA or 2,6-DMHA gave almost pure nonanoic acid homopolymers, but the other branched substrates produced polymers which contained the type of methyl branching expected from the starting alkanolic acid. The melting points,  $T_m$ , of most polymers were similar to that of the nonanoic acid polymer except for that of the polymer from 6-MNA the  $T_m$  was considerably higher, and this polymer also crystallized much faster than the others even though the 6-methylnonanoate units in the polymer included equal amounts of the two chiral isomers.

Our studies on the microbial polymer cellular inclusions were focused primarily on the structural and functional role of the protein components. Antibodies to each of the polypeptides were prepared and immunoassay techniques were established for the rapid identification of the polymerase and depolymerase enzymes. This technology (i.e., having Elisa assays available) will accelerate the determination of the primary and secondary structures of these two enzyme systems. Amino acid composition and sequencing studies were carried out. The isolation and analysis of a non-enzymatic protein, which may play a role in the assembly and organization of the granule, was also accomplished.

In our studies on the enzymatic degradation of PHAs we followed the course of the degradation by scanning electron microscopy, SEM. The SEM studies of biodegraded PHB/V films indicated that amorphous regions biodegraded faster than the crystalline regions. This conclusion was implied by micrographs of originally smooth surfaces which, when degraded, revealed what appeared to be crystallites surrounded by roughened, degraded areas. Also, biodegradation may have started at the hydroxyl group terminus and proceeded in a linear fashion along the length of the chain. This mechanism was indicated by the retardation of degradation when the chain ends were blocked by heptafluorobutyl chloride labeling.

SIGNIFICANCE: The information gained from these studies will be of great importance for the scale-up and development of new PHAs which may find practical applications in the plastics industry and in medicine.

PUBLICATIONS:

1. Lenz, R.W., R.A. Gross, R.C. Fuller and H. Brandl. (1988) Bioresorbable polyesters from bacterial polymerization reactions. "Polymers in Medicine", III, C. Magliaresi (ed.), Elsevier Science Publishers, Amsterdam, 19-26.
2. Brandl, H., R.A. Gross, R.W. Lenz and R.C. Fuller. (1988) *Pseudomonas oleovorans* as a source of poly( $\beta$ -hydroxyalkanoates) for potential applications as biodegradable polyesters. Applied and Environmental Microbiology, 54, 1977-1982.
3. Brandl, H., R.A. Gross, R.W. Lenz and R.C. Fuller. (1988) *Pseudomonas oleovorans* as a source for novel poly( $\beta$ -hydroxyalkanoates). Polymer Preprints, 29, 590.
4. Gross, R.A., H. Brandl, H.W. Ulmer, D.J. Tshudy, P.C. Uden, R.C. Fuller and R.W. Lenz. (1989) The incorporation of deuterium into poly( $\beta$ -hydroxybutyrate) produced by *Rhodobacter sphaeroides*. Polymer Preprints, 30, 398-399.
5. Brandl, H., E.J. Knee, R.C. Fuller, R.A. Gross and R.W. Lenz. (1989) Ability of the phototrophic bacterium *Rhodospirillum rubrum* to produce various poly( $\beta$ -hydroxyalkanoates): potential sources for biodegradable polyesters. Int. J. Biol. Macromol., 11, 49-55.
6. Gross, R.A., C. DeMello, R.W. Lenz, H. Brandl and R.C. Fuller. (1989) Biosynthesis and characterization of poly( $\beta$ -hydroxyalkanoates) produced by *Pseudomonas oleovorans*. Macromolecules, 22, 1106-1115.
7. Gross, R.A., H. Brandl, H.W. Ulmer, M.A. Posada, R.C. Fuller and R.W. Lenz. (1989) The biosynthesis and characterization of new poly( $\beta$ -hydroxyalkanoates). Polymer Preprints, 30, 492-494.
8. Lenz, R.W., R.A. Gross, H. Brandl and R.C. Fuller. (1989) Poly( $\beta$ -hydroxyalkanoates): natural biocompatible and biodegradable polyesters produced by bacteria. Chinese Journal of Polymer Science, 7, 289-298.
9. Brandl, H., R.A. Gross, R.W. Lenz and R.C. Fuller. (1990) Plastics from bacteria and for bacteria: poly( $\beta$ -hydroxyalkanoates) as natural, biocompatible, and biodegradable polyesters. Advances in Biochemical Engineering/Biotechnology, 41, 77-93.
10. Fritzsche, K., R.W. Lenz and R.C. Fuller. (1990) Bacterial polyesters containing branched poly( $\beta$ -hydroxyalkanoate) units. Int. J. Biol. Macromol., 12, 92-101.
11. Fritzsche, K., R.W. Lenz and R.C. Fuller. (1990) Production of unsaturated polyesters by *Pseudomonas oleovorans*. Int. J. Biol. Macromol., 12, 85-91.

12. Fritzsche, K., R.W. Lenz and R.C. Fuller. (1990) An unusual bacterial polyester with a phenyl pendant group. Makromol. Chem., 191, 1957-1965.
13. Ballistreri, A., G. Montaudo, G. Impallomeni, R.W. Lenz, Y.B. Kim and R.C. Fuller. (1990) Sequence distribution of  $\beta$ -hydroxyalkanoate units with higher alkyl groups in bacterial copolyesters. Macromolecules, 23, 5059-5064.
14. Lenz, R.W., B.-W. Kim, H.W. Ulmer, K. Fritzsche, E. Knee and R.C. Fuller. (1990) Functionalized poly- $\beta$ -hydroxyalkanoates produced by bacteria. "Novel Biodegradable Microbial Polymers", E.A.Dawes (ed.), Kluwer Academic Publishers, 23-35.
15. Lenz, R.W. (1990) Biodegradation of microbial copolyesters: poly(3-hydroxybutyrate-co-3-hydroxyvalerate) and poly(3-hydroxybutyrate-co-4-hydroxybutyrate). Chemtracts: Macromol. Chem., 1, 343-345.
16. Brandl, H., R.A. Gross, R.W. Lenz, R. Lloyd and R.C. Fuller. (1991) The accumulation of poly(3-hydroxyalkanoates) in *Rhodobacter sphaeroides*. Archives of Microbiology, 155, 337-340.
17. Liebergesell, M., E. Hustede, A. Timm, A. Steinbüchel, R.C. Fuller, R.W. Lenz and H.G. Schlegel. (1991) Formation of poly(3-hydroxyalkanoates) by phototrophic and chemolithotrophic bacteria. Archives of Microbiology, 155, 415-421.
18. Benvenuti and R.W. Lenz. (1991) Polymerization and copolymerization of  $\beta$ -butyrolactone and benzyl- $\beta$ -malolactonate by aluminoxane catalysts. J. Polymer Sci., Part A: Polymer Chem., 29, 793-805.
19. Kim, Y.B., R.W. Lenz and R.C. Fuller. (1991) Preparation and characterization of poly( $\beta$ -hydroxyalkanoates) obtained from *Pseudomonas oleovorans* grown with mixtures of 5-phenylvaleric acid and n-alkanoic acids. Macromolecules, 24, 5256-5260.
20. Ballistreri, A., G. Montaudo, M. Giuffrida, R.W. Lenz and R.C. Fuller. (1991) Determination of sequence distributions in bacterial copolyesters containing higher alkyl and alkenyl pendant groups. Macromolecules, 25, 1845-1851.
21. Kim, Y.B., R.W. Lenz, and R.C. Fuller. (1991) Polyesters produced by microorganisms. Journal of Bioactive and Compatible Polymers, 6, 382-392.
22. Antoun, S., I. Grizzi, R.W. Lenz and R.C. Fuller. (1991) Poly- $\beta$ -hydroxyalkanoate copolymers containing brominated repeating units produced by *Pseudomonas oleovorans*. Chirality, 3, 492-494.
23. Lenz, R.W., H. Ulmer, Y.B. Kim and R.C. Fuller. (1992) Production of non-natural and functional poly- $\beta$ -hydroxyalkanoates by bacteria. "Contemporary Topics in Polymer Science, Vol. 7", J.C. Salamone and J. Riffle (eds.), Plenum Press, 307-315.

24. Kim, Y.B., R.W. Lenz and R.C. Fuller. (1992) Poly( $\beta$ -hydroxyalkanoate) copolymers containing brominated repeating units produced by *Pseudomonas oleovorans*. Macromolecules, 25, 1852-1857.
25. Richtering, H.W., K.D. Gagnon, R.W. Lenz, R.C. Fuller and H.H. Winter. (1992) Physical gelation of a bacterial thermoplastic elastomer. Macromolecules, 25, 2429-2433.
26. Gilmore, D.F., S. Antoun, R.W. Lenz, S. Goodwin, R. Austin and R.C. Fuller. (1992) The fate of 'biodegradable' plastics in municipal leaf compost. Journal of Industrial Microbiology, 10, 199-206.
27. Lenz, R.W., Y.B. Kim and R.C. Fuller. (1992) Production of unusual bacterial polyesters by *Pseudomonas oleovorans* through cometabolism. FEMS Microbiology Reviews, 103, 207-214.
28. Fuller, R.C., J.P. O'Donnell, J. Saulnier, T.E. Redlinger, J. Foster and R.W. Lenz. (1992) The supramolecular architecture of the polyhydroxyalkanoate inclusions in *Pseudomonas oleovorans*. FEMS Microbiology Reviews, 103, 279-288.
29. Gross, R.A., H. Ulmer, R.W. Lenz, D.J. Tshudy, P.C. Uden, H. Brandl and R.C. Fuller. (1992) Biodeuteration of poly( $\beta$ -hydroxybutyrate). Int. J. Biol. Macromol., 14, 33-40.
30. Richtering, H.W., K.D. Gagnon, R.W. Lenz, R.C. Fuller and H.H. Winter. (1992) Physical gelation of a bacterial thermoplastic elastomer. Macromolecules, 25, 2429-2433.
31. Lenz, R.W., B.-W. Kim, H.W. Ulmer, K. Fritzsche and R.C. Fuller. (1990) Functionalized poly- $\beta$ -hydroxyalkanoates produced by bacteria. Polymer Preprints, 31, 408-409.
32. Knee, E.J., M. Wolf, R.W. Lenz and R.C. Fuller. (1990) Influence of growth conditions on production and composition of PHA by *Pseudomonas oleovorans*. "Novel Biodegradable Microbial Polymers", E.A.Dawes (ed.), Kluwer Academic Publishers, 439-440.
33. Ulmer, H.W., R.A. Gross, P. Wiesbach, R.C. Fuller and R.W. Lenz. (1989) The bacterial synthesis of functional poly( $\beta$ -hydroxyalkanoates). Polymer Preprints, 30, 402-403.